



**Technical and Test Institute
for Construction Prague**

Prosecká 811/76a
190 00 Prague
Czech Republic
eota@tzus.cz



Member of



www.eota.eu

European Technical Assessment

**ETA 16/0676
of 10/08/2016**

Technical Assessment Body issuing the ETA: Technical and Test Institute
for Construction Prague

Trade name of the construction product

ESSVE ECM

**Product family to which the construction
product belongs**

Product area code: 33
Bonded injection type anchor for use
in non-cracked concrete

Manufacturer

ESSVE Produkter AB
SE-164 07 Kista
Esbogatan 14
Sweden

Manufacturing plant

Essve Produkter AB Plant 403-2

**This European Technical Assessment
contains**

15 pages including 11 Annexes which form
an integral part of this assessment

**This European Technical Assessment is
issued in accordance with regulation
(EU) No 305/2011, on the basis of**

ETAG 001-Part 1 and Part 5, edition 2013,
used as European Assessment Document
(EAD)

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body - Technical and Test Institute for Construction Prague. Any partial reproduction has to be identified as such

1. Technical description of the product

The ESSVE ECM for non-cracked concrete is a bonded anchor consisting of a cartridge with injection mortar and a steel element. The steel elements consists of a commercial threaded rods, a hexagon nut and a washer. The steel elements are made of galvanised steel or stainless steel.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The illustration and the description of the product are given in Annex A.

2. Specification of the intended use in accordance with the applicable EAD

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The provisions made in this European Technical Assessment are based on an assumed working life of the anchor of 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the products in relation to the expected economically reasonable working life of the works.

3. Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance for tension loads	See Annex C 1
Characteristic resistance for shear loads	See Annex C 2
Displacement	See Annex C 3

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchorage satisfy requirements for Class A1
Resistance to fire	No performance assessed

3.3 Hygiene, health and environment (BWR 3)

Regarding dangerous substances contained in this European Technical Assessment, there may be requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.

3.4 Safety in use (BWR 4)

For basic requirement safety in use the same criteria are valid as for Basic Requirement Mechanical resistance and stability.

3.5 Sustainable use of natural resources (BWR 7)

For the sustainable use of natural resources no performance was determined for this product.

3.6 General aspects relating to fitness for use

Durability and serviceability are only ensured if the specifications of intended use according to Annex B 1 are kept.

4. **Assessment and verification of constancy of performance (AVCP) system applied with reference to its legal base**

According to the Decision 96/582/EC of the European Commission¹ the system of assessment verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) given in the following table apply.

Product	Intended use	Level or class	System
Metal anchors for use in concrete	For fixing and/or supporting to concrete, structural elements (which contributes to the stability of the works) or heavy units	-	1

5. **Technical details necessary for the implementation of the AVCP system, as provided in the applicable EAD**

5.1 **Tasks of the manufacturer**

The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this European Technical Assessment.

The manufacturer may only use raw materials stated in the technical documentation of this European Technical Assessment.

The factory production control shall be in accordance with the control plan which is a part of the technical documentation of this European Technical Assessment. The control plan is laid down in the context of the factory production control system operated by the manufacturer and deposited at Technický a zkušební ústav stavební Praha, s.p.² The results of factory production control shall be recorded and evaluated in accordance with the provisions of the control plan.

The manufacturer shall, on the basis of a contract, involve a body which is notified for the tasks referred to in section 4 in the field of anchors in order to undertake the actions laid down in section 5.2. For this purpose, the control plan referred to in this section and section 5.2 shall be handed over by the manufacturer to the notified body involved.

The manufacturer shall make a declaration of performance, stating that the construction product is in conformity with the provisions of this European Technical Assessment.

¹ Official Journal of the European Communities L 254 of 08.10.1996

² The control plan is a confidential part of the documentation of the European Technical Assessment, but not published together with the ETA and only handed over to the approved body involved in the procedure of AVCP.

5.2 Tasks of the notified bodies

The notified body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report.

The notified certification body involved by the manufacturer shall issue a certificate of constancy of performance of the product stating the conformity with the provisions of this European Technical Assessment.

In cases where the provisions of the European Technical Assessment and its control plan are no longer fulfilled the notified body shall withdraw the certificate of constancy of performance and inform Technický a zkušební ústav stavební Praha, s.p without delay.


Issued in Prague on 10.08.2016

By

Ing. Mária Schaan

Head of the Technical Assessment Body

Installation threaded rod



h_{ef} = effective setting depth
 h_0 = bore hole depth
 t_{fix} = thickness of fixture
 h_{min} = thickness of member

ESSVE ECM	Annex A 1
Product description Installed conditions	

Cartridge: ESSVE ECM

150 ml, 280 ml, 300 ml up to 330 ml and 380 ml up to 420 ml cartridge (Type: coaxial)


Sealing/Screw cap



Imprint: ESSVE ECM
processing notes, charge-code, shelf life, hazard-code,
curing- and processing time (depending on the
temperature), with as well as without travel scale

235 ml, 345 ml up to 360 ml and 825 ml cartridge (Type: "side-by-side")


Sealing/Screw cap



Imprint: ESSVE ECM
processing notes, charge-code, shelf life, hazard-code,
curing- and processing time (depending on the
temperature), with as well as without travel scale


165 ml and 300 ml cartridge (Type: "foil tube")

Sealing/Screw cap



Imprint: ESSVE ECM
processing notes, charge-code, shelf life, hazard-code,
curing- and processing time (depending on the
temperature), with as well as without travel scale

Static mixer




ESSVE ECM

Product description
Injection system

Annex A 2

Threaded rod M8, M10, M12, M16, M20, M24 with washer and hexagon nut



Commercial standard threaded rod with:

- Materials, dimensions and mechanical properties acc. Table A1
- Inspection certificate 3.1 acc. To EN 10204:2004
- Marking of embedment depth

ESSVE ECM

Product description
Threaded rod

Annex A 3

Table A1: Materials

Part	Designation	Material
Steel, zinc plated $\geq 5 \mu\text{m}$ acc. to EN ISO 4042:1999 or Steel, hot-dip galvanized $\geq 40 \mu\text{m}$ acc. to EN ISO 10684:2004+AC:2009		
1	Anchor rod	Steel, EN 10087:1998 or EN 10263:2001 Property class 5.8, 8.8 EN1993-1-8:2005+AC:2009
2	Hexagon nut, EN ISO 4032:2012	Steel acc. to EN10087:1998 or EN10263:2001 Property class 5 (for 5.8 rod) EN ISO 898-2:2012, Property class 8 (for 8.8 rod) EN ISO 898-2:2012
3	Washer, EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 or EN ISO 7094:2000	Steel, zinc plated or hot-dip galvanised
Stainless Steel		
1	Anchor rod	Material A2-70, A4-70, A4-80, EN ISO 3506
2	Hexagon nut, EN ISO 4032:2012	Material according to threaded rod
3	Washer, EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 or EN ISO 7094:2000	Material according to threaded rod
High corrosion resistance steel		
1	Anchor rod	Material 1.4529 / 1,4565, EN 10088-1:2005, Property class 70 EN ISO 3506-1:2009
2	Hexagon nut, EN ISO 4032:2012	Material 1.4529 / 1,4565, EN 10088-1:2005, Property class 70 (for class 70 rod) EN ISO 3506-1:2009
3	Washer, EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 or EN ISO 7094:2000	Material 1.4529 / 1,4565, EN 10088-1:2005,

ESSVE ECM**Product description**
Materials**Annex A 4**

Specifications of intended use

Anchorage subject to:

- Static and quasi-static loads

Base materials

- Reinforced or unreinforced normal weight concrete according to EN 206-1:2000.
- Strength classes C20/25 to C50/60 according to EN 206-1:2000
- Non-cracked concrete

Temperature range:

- I: -40°C to +40°C (max. long. term temperature +24°C and max. short term temperature +40°C)
- II: -40°C to +80°C (max. long. term temperature +50°C and max. short term temperature +80°C)

Use conditions (Environmental conditions)

- Structures subject to dry internal conditions (zinc coated steel, stainless steel).
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions exist (high corrosion resistant steel).

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

Design:

- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Anchorages under static or quasi static actions are designed in accordance with:
 - EOTA Technical Report TR029 "Design of bonded anchors", Edition September 2010 or
 - CEN/TS 1992-4:2009

Installation:

- Dry, wet or flooded holes concrete.
- Hole drilling by hammer or compressed air drill mode.
- Overhead installation allowed
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.

ESSVE ECM

Intended use
Specifications

Annex B 1

Table B1: Installation parameters for threaded rod

Anchor Size		M8	M10	M12	M16	M20	M24
Nominal drill hole diameter	d_0 [mm] =	10	12	14	18	22	28
Effective anchorage depth	$h_{ef,min}$ [mm] =	64	80	96	128	160	192
	$h_{ef,max}$ [mm] =	96	120	144	192	240	288
Diameter of clearance hole in the fixture	d_f [mm] ≤	9	12	14	18	22	26
Diameter of steel brush	d_b [mm] ≥	12	14	16	20	26	30
Torque moment	T_{inst} [Nm] ≤	10	20	40	80	150	200
Thickness of fixture	$t_{fix,min}$ [mm] >	0					
	$t_{fix,max}$ [mm] <	1500					
Thickness of member	h_{min} [mm]	$h_{ef} + 30 \text{ mm} \geq 100 \text{ mm}$				$h_{ef} + 2d_0$	
Minimum spacing	s_{min} [mm]	50	60	70	95	120	145
Minimum edge distance	c_{min} [mm]	50	60	70	95	120	145

Steel brush



Table B2: Parameter cleaning and setting tools

Threaded Rod	d_0 Drill bit - ϕ	d_b Brush - ϕ	$d_{b,min}$ min. Brush - ϕ
(mm)	(mm)	(mm)	(mm)
M8	10	12	10.5
M10	12	14	12.5
M12	14	16	14.5
M16	18	20	18.5
M20	22	26	24.5
M24	28	30	28.5



Hand pump (volume 750 ml)
Drill bit diameter (d_0): 10 mm to 20 mm



Recommended compressed air tool (min 6 bar)
Drill bit diameter (d_0): 10 mm to 26 mm


ESSVE ECM

Intended use


Installation parameters
Cleaning and setting tools

Annex B 2

Assembly instructions




- 1 Drill with hammer drill a hole into the base material to the size and embedment depth required by the selected anchor (Table B1). In case of aborted drill hole: the drill hole shall be filled with mortar.




- 2a Starting from the bottom or back of the bore hole, blow the hole clean with compressed air or a hand pump (Annex B 2) a minimum of four times. If the bore hole ground is not reached an extension shall be used.


or



The hand pump can be used for anchor sizes up to bore hole diameter 20 mm. For bore holes larger than 20 mm or deeper 240 mm, compressed air (min. 6 bar) must be used.




- 2b Check brush diameter (Table B2) and attach the brush to a drilling machine or a battery screwdriver. Brush the hole with an appropriate sized wire brush > db,min (Table B2) a minimum of four times. If the bore hole ground is not reached with the brush, a brush extension shall be used (Table B2).




- 2c Finally blow the hole clean again with compressed air or a hand pump (Annex B 2) a minimum of four times. If the bore hole ground is not reached an extension shall be used.

The hand pump can be used for anchor sizes up to bore hole diameter 20 mm. For bore holes larger than 20 mm or deeper 240 mm, compressed air (min. 6 bar) must be used.


or




After cleaning, the bore hole has to be protected against re-contamination in an appropriate way, until dispensing the mortar in the bore hole. If necessary, the cleaning repeated has to be directly before dispensing the mortar. In-flowing water must not contaminate the bore hole again



- 3 Attach a supplied static-mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. For foil tube cartridges, cut off the foil tube clip before use. For every working interruption longer than the recommended working time (Table B3) as well as for new cartridges, a new static-mixer shall be used.



- 4 Prior to inserting the anchor rod into the filled bore hole, the position of the embedment depth shall be marked on the anchor rods




- 5 Prior to dispensing into the anchor hole, squeeze out separately a minimum of three full strokes and discard non-uniformly mixed adhesive components until the mortar shows a consistent grey colour. For foil tube cartridges is must be discarded a minimum of six full strokes.

ESSVE ECM


Intended use
Installation instructions

Annex B 3


Assembly instructions (continuation)




- 6 Starting from the bottom or back of the cleaned anchor hole fill the hole up to approximately two-thirds with adhesive. Slowly withdraw the static mixing nozzle as the hole fills to avoid creating air pockets. For embedment larger than 190 mm an extension nozzle shall be used. Observe the gel-Working times given in Table B3.




- 7 Push the threaded rod into the anchor hole while turning slightly to ensure positive distribution of the adhesive until the embedment depth is reached.



- 8 The anchor should be free of dirt, grease, oil or other foreign material. Be sure that the anchor is fully seated at the bottom of the hole and that excess mortar is visible at the top of the hole. If these requirements are not maintained, the application has to be renewed. For overhead application the anchor rod should be fixed (e.g. wedges).



- 9 Allow the adhesive to cure to the specified time prior to applying any load or torque. Do not move or load the anchor until it is fully cured (attend Table B3).



- 10 After full curing, the add-on part can be installed with the max. torque (Table B1) by using a calibrated torque wrench.

Table B3: Minimum curing time

Concrete temperature [°C]	ESSVE ECM	
	Working time [min]	Minimum curing time [min]
+5 to +9	10	145
+10 to +14	8	85
+15 to +19	6	70
+20 to +29	4	50
+30 to +34	3	35
+35 to +39	3	20
Cartridge temperature	+5°C to +30°C	

ESSVE ECM

Intended use

Installation instructions (continuation)

Curing time

Annex B 4

Table C1: Characteristic values of resistance for threaded rods under tension loads in non-cracked concrete

Anchor size threaded rod				M8	M10	M12	M16	M20	M24
Steel failure									
Characteristic tension resistance		N _{Rk,s}	[kN]	A _s x f _{uk}					
Combined pullout and concrete cone failure									
Temperature range I: 40°C/24°C	dry and wet concrete	τ _{Rk,uncr}	[N/mm ²]	8.0	7.0	7.0	7.0	7.0	6.0
	flooded bore hole	τ _{Rk,uncr}	[N/mm ²]	8.0	7.0	7.0	7.0	7.0	6.0
Temperature range II: 80°C/50°C	dry and wet concrete	τ _{Rk,uncr}	[N/mm ²]	6.5	6.0	6.0	6.0	6.0	6.0
	flooded bore hole	τ _{Rk,uncr}	[N/mm ²]	6.5	6.0	6.0	6.0	6.0	6.0
Increasing factor for concrete Ψ _c		C25/30		1.04					
		C30/37		1.08					
		C35/45		1.13					
		C40/50		1.15					
		C45/55		1.17					
		C50/60		1.19					
Factor according to CEN/TS 1992-4-5 Section 6.2.2.3		k ₈	[-]	10.1					
Concrete cone failure									
Factor according to CEN/TS 1992-4-5 Section 6.2.2.1		k _{ucr}	[-]	10.1					
Edge distance		c _{cr,N}	[mm]	1.5 h _{ef}					
Axial distance		s _{cr,N}	[mm]	3.0 h _{ef}					
Splitting Failure									
Edge distance		c _{cr,sp}	[mm]	2.0 h _{ef}			1.5 h _{ef}		
Axial distance		s _{cr,sp}	[mm]	2 c _{cr,sp}					
Installation safety factor (dry and wet concrete)		γ ₂ = γ _{inst}		1.0					
Installation safety factor (flooded bore hole)		γ ₂ = γ _{inst}		1.2					

ESSVE ECM

Performances

Characteristic values of resistance under tension loads in non-cracked concrete

Annex C 1

Table C2: Characteristic values of resistance for threaded rods under shear loads in non-cracked concrete

Anchor size threaded rod			M8	M10	M12	M16	M20	M24
Steel failure without lever arm								
Characteristic tension resistance	$V_{Rk,s}$	[kN]	$0.5 \times A_s \times f_{uk}$					
Ductility factor according to CEN/TS 1992-4-5 Section 6.3.2.1	k_2		0.8					
Steel failure with lever arm								
Characteristic bending moment	$M^0_{Rk,s}$	[Nm]	$1.2 \times W_{el} \times f_{uk}$					
Concrete pry-out failure								
Factor k in equation (27) of CEN/TS 1992-4-5 Section 6.3.3 Factor k in equation (5.7) of Technical Report TR 029	$k_{(3)}$	[-]	2.0					
Installation safety factor	$\gamma_2 = \gamma_{inst}$		1.0					
Concrete edge failure								
Effective length of anchor	l_f	[mm]	$l_f = \min(h_{ef} ; 8 d_{nom})$					
Outside diameter of anchor	d_{nom}	[mm]	8	10	12	16	20	24
Installation safety factor	$\gamma_2 = \gamma_{inst}$		1.0					

ESSVE ECM

Performances

Characteristic values of resistance under shear loads in non-cracked concrete

Annex C 2

Table C3: Displacement under tension load¹⁾ (threaded rod)

Anchor size threaded rod			M8	M10	M12	M16	M20	M24
Non-cracked concrete C20/25								
Tension load	F	[kN]	6.3	6.3	9.9	19.8	29.8	37.7
Displacement	δ_{N0}	[mm]	0.1	0.1	0.2	0.5	0.6	0.8
	$\delta_{N\infty}$	[mm]	0.4	0.4	0.4	0.4	0.4	0.4

¹⁾Calculation of the displacement

$\delta_{N0} = \delta_{N0} - \text{factor} \times \tau$;

$\delta_{N\infty} = \delta_{N\infty} - \text{factor} \times \tau$;

Table C4: Displacement under shear load¹⁾ (threaded rod)

Anchor size threaded rod			M8	M10	M12	M16	M20	M24
Non-cracked concrete C20/25								
Shear load	F	[kN]	5.2	8.3	12.0	22.4	35.0	50.4
Displacement	Δ_{V0}	[mm]	0.1	0.2	0.3	0.5	0.8	0.9
	$\Delta_{V\infty}$	[mm]	0.2	0.3	0.5	0.8	1.2	1.4

¹⁾Calculation of the displacement

$\Delta_{V0} = \delta_{V0} - \text{factor} \times V$;

$\Delta_{V\infty} = \delta_{V\infty} - \text{factor} \times V$;

ESSVE ECM

Performances
Displacement

Annex C 3